

# Deck



**REFIN**  
CERAMICHE







Flare 225mm x 900mm / LZ27  
9" x 36"



Flare 225mm x 900mm LZ27  
9" x 36"



Bright 225mm x 900mm LZ23  
9" x 36"



Dusk 225mm x 900m LZ26  
9" x 36"



Flare 225mm x 900mm / LZ27  
9" x 36"





Bright 225mm x 900mm / LZ23  
9" x 36"






Dusk 225mm x 900mm / LZ26  
9" x 36"



18,99 €



20,99 €














24,99 €










## Technical Features - EN 14411-G ISO 13006-G

	Regulation	Required standards	Refin Value	
 <b>Sizes</b>	UNI EN ISO 10545/2	Not rectified	Rectified	
		→ Length and width	± 0,6 % max 2mm	± 0,3 % max 1mm
		→ Thickness	± 5 % max 0,5mm	± 5 % max 0,5mm
		→ Linearity	± 0,5 % max 1,5mm	± 0,3 % max 0,8mm
		→ Wedging	± 0,5 % max 2mm	± 0,3 % max 1,5mm
		→ Warpage	± 0,5 % max 2mm	± 0,4 % max 1,8mm
 <b>Water absorption</b>	UNI EN ISO 10545/3	≤ 0,5 %	0,2%	
 <b>Flexual Streight</b>	UNI EN ISO 10545/4	≥ 35 N/mm <sup>2</sup>	Conforme Compliant	
		S ≥ 1300 N (thickness ≥ 7,5 mm)	Conforme Compliant	
 <b>Coefficient of restitution (COR)</b>	UNI EN ISO 10545/5	Recommended value ≥ 0,55/	Conforme Compliant	
 <b>Deep abrasion resistance</b>	UNI EN ISO 10545/6	≤ 175 mm <sup>3</sup>	Conforme Compliant	
 <b>Abrasion resistance</b>	UNI EN ISO 10545/7	Only for glazed tiles		
 <b>Coefficient of thermal linear expansion</b>	UNI EN ISO 10545/8	Tests method available	≤ 7 · MK <sup>-1</sup>	
 <b>Thermal shock resistance</b>	UNI EN ISO 10545/9	No sample must show visible defects	Conforme Compliant	
 <b>Moisture expansion</b>	UNI EN ISO 10545/10	Tests method available	≤ 0,01 % (0,1 mm/m)	
 <b>Fire resistance</b>	UNI EN ISO 13501-1	Declare a value Class A1 or A <sub>1fl</sub>	A1 <sup>n</sup>	
 <b>Frost resistance</b>	UNI EN ISO 10545/12	Resistant	Conforme Compliant	

## Technical Features - EN 14411-G ISO 13006-G

	Regulation	Required standards	Refin Value	
 <b>Chemical resistance</b>	UNI EN ISO 10545/13	Resistance to household chemicals and swimming pool salts	Minimum class B (GB for glazed tiles) Minimum class B (UB for unglazed tiles) Conforme Compliant	
		Resistance to low concentrations of acids and alkalis	Declare a class Tests method available ULA	
		Resistance to high concentrations of acids and alkalis	Declare a class Tests method available UHA	
			UGL Declare a value Class 5	
 <b>Flexual Streight</b>	UNI EN ISO 10545/14	UGL Declare a value	Class 5	
		GL ≥ 3		
 <b>Lead and cadmium discharge</b>	UNI EN ISO 10545/15	Declared value for GL tiles		
 <b>Assessment of slip resistance</b>	DIN 51130	Declare a value (R)	R10	
		DIN 51097	Declare a value (A+B+C)	A+B
		BS 7976-2:2002 (CEN/TS 16165, Annex C) Pendulum Friction Test	Declare a value	
 <b>Measurement of dynamic coefficient of friction</b>	B.C.R.A. Rep. CEC/81	Asciutto >0.40 / Bagnato > 0.40	Conforme Compliant	
		ANSI A 137.1-2012(BOT3000)	>0.42 Wet	Conforme Compliant





**REFIN**  
CERAMICHE



**Ceramiche Refin S.P.A.**

**P.IVA 00935330357 - CF: 03047170372  
Tel. +39 0522 990499**

**Registered office**

**Via I Maggio, 22 Salvaterra  
42013 Casalgrande (RE) Italy**

**Company showroom**

**Via G. Ambrosoli, 2 Salvaterra  
42013 Casalgrande (RE) Italy**

